



PRODUCT DESCRIPTION

LOCTITE® 5651 provides the following product characteristics:

Technology	Acrylic
Chemical Type	Methacrylate Ester
Appearance (uncured)	White to off-white paste
Components	One component-requires no mixing
Viscosity	Medium
Cure	Anaerobic
Secondary Cure	Activator
Application	Thread Sealing
Strength	Low

LOCTITE® 5651 is designed for the locking and sealing of metal pipes and fittings. The product cures when confined in the absence of air between close fitting metal surfaces and prevents loosening and leakage from shock and vibration.

Pressure Resistance

LOCTITE® 5651 was successfully tested for pressure resistance and sealability to 20 MPa or 3 MPa by instant sealing.

3/4 inch steel pipe tees and plugs were assembled and torqued to 60 N-m and allowed to cure for 72 hours prior to testing at 20 MPa water pressure.

3/4 inch steel pipe tees and plugs were assembled and torqued to 60 N-m and allowed to cure for 5 minutes prior to testing at 3 MPa water pressure.


PROPERTIES OF UNCURED MATERIAL

	Typical Value
Specific Gravity @ 25 °C	1.17
Flash Point – See MSDS	
Viscosity, @ 25 °C, mPa·s (cP)	
Brookfield RVT	
Spindle 6 @ 2.5 rpm	100,000

TYPICAL CURING PERFORMANCE


Cure speed vs. substrate

The rate of cure will depend on substrate used. The graph below shows the breakaway torque strength developed with time on M10 mild steel nuts & bolts compared to stainless steel and tested according to ISO 10964.



Cure speed vs. temperature


The rate of cure will depend on the temperature. The graph below shows the breakaway torque strength developed with time on M10 mild steel nuts & bolts and tested.




Cure speed vs. activator

Where cure speed is unacceptably long, or large gaps are present, applying activator to the surface will improve cure speed.

The graph below shows the breakaway torque strength developed with time at 23 °C on M10 stainless steel nuts & bolts and tested.



The graph below shows the breakaway torque strength developed with time at 5 °C on M10 mild steel nuts & bolts and tested.



TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Coefficient of Thermal Expansion, ASTM D696, K ⁻¹	80 x 10 ⁻⁶
Coefficient of Thermal Conductivity, ASTM C117, W/(m·K)	0.10
Specific Heat, kJ/(kg·K)	0.30

PERFORMANCE OF CURED MATERIAL

(After 72 hrs at 23 °C on M10 mild steel nuts & bolts)

Breakaway torque, ISO 10964, N·m	Typical Value 9
----------------------------------	--------------------

TYPICAL ENVIRONMENTAL RESISTANCE


Test Procedure : Breakloose torque on fasteners seated to 5N·m, ISO 10964

Substrate: M10 degreased steel fasteners

Cure procedure: 72 hours at 23 °C


Hot Strength

Tested at temperature.



Heat Aging

Aged at temperature indicated and tested at 23 °C



Chemical / Solvent Resistance

Aged under conditions indicated and tested at 23 °C

Solvent	Temp.	% Initial Strength retained after 30 days
Isopropyl alcohol	23 °C	100
Acetone	23 °C	57
Distilled water	87 °C	100
LLC (Water/Glycol)	87 °C	100

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents which may cover such processes or compositions. We recommend that each prospective user test his proposed applications before repetitive use, using this data as a guide. This product may be covered by one or more patents or patent applications.

Trademark usage

LOCTITE is a trademark of Henkel Corporation